	L #	Hits	Search Text	DBs
1	L1	8942 68	@pd>"20051206"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
2	L2	1869	((523/160) or (523/161)).CCLS.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
3	L3	589	(106/31.27).CCLS.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
4	L4	4198	((524/505) or (524/556) or (524/560)).CCLS.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
5	L5	119	1 and 2	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
6	L6	46	1 and 3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
7	L7	103	1 and 4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
8	L8	1374 97	block near5 (polymer or copolymer) or diblock or triblock or ab1 or bab! or aba!	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
9	L10	4293 7	colored near5 (polymer or resin or particle or block or copolymer or particulate)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
10	L11	2652	(coemulsif$7 or co adj emulsif$7)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
11	L12	0	5 and 8 and 10 and 11	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
12	L13	9	5 and 8 and 10	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
13	L14	4	6 and 8 and 10	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
14	L15	1	7 and 8 and 10	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
15	L16	33028	(dyed or pigmented or colored) near5 (resin or polymer or copolymer)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
16	L17	159	colored near5 (resin or polymer or particle) same (emulsification or emulsify)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
17	L18	64	colored near5 (resin or polymer or particle) same add$3 near5 water near5 solvent	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
18	L19	692	colored near5 (resin or polymer or particle) and add$3 near5 water near5 solvent	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
19	L20	22	colored near5 (polymer or resin or particle or block or copolymer) and monomer same dye same (emulsify or emulsification)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
20	L21	2	colored near5 (polymer or resin or particle or block or copolymer) and block same dye same (emulsify or emulsification)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
21	L22	30	(5 6 7) and (16 17 18 19 20 21)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
22	L23	1	1 and 8 and 10 and 11	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
23	L26	161	colored near5 (polymer or resin or particle or block or copolymer or particulate) same (emulsification or emulsify)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
24	L27	66	colored near5 (polymer or resin or particle or block or copolymer or particulate) same add$3 near5 water near5 solvent	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
25	L28	725	colored near5 (polymer or resin or particle or block or copolymer or particulate) and add$3 near5 water near5 solvent	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
26	L29	22	colored near5 (polymer or resin or particle or block or copolymer or particulate) and monomer same dye same (emulsify or emulsification)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
27	L30	2	colored near5 (polymer or resin or particle or block or copolymer or particulate) and block same dye same (emulsify or emulsification)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
28	L31	60	1 and (26 27 28 29 30)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
29	L24	197	1 and 8 and 10	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
30	L32	6	colored near5 (polymer or resin or particle or copolymer or particulate) with (block or diblock or triblock) and 1	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
31	L33	108	colored near5 (polymer or resin or particle or copolymer or particulate) with (block or diblock or triblock) and ink	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
32	L34	2	("2002/0032252").URPN.	USPAT
33	L35	39	colored near5 block adj copolymer	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
34	L37	1	36 and 11	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
35	L38	2	36 and (emulsification or emulsify)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
36	L39	16	36 andadd$3 near5 water near5 solvent	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
37	L40	1	36 and add$3 near5 water near5 solvent	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
38	L36	16	35 and dye	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
39	L41	6	(emulsif$7 or emulsify$3) same water same solvent same dye same block	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
40	L42	161	(emulsif$7 or emulsify$3) same water same solvent same dye and 10	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
41	L43	59	42 and 8	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
42	L44	623	(inkjet or ink near3 jet) and dye and 8 and 10	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
43	L45	47	1 and 44	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
44	L46	40	(inkjet or ink near3 jet) and dye and 8 same 10	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
45	L47	78	2 and 44	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
46	L48	2	("6664312").PN.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
47	L49	1	48 and dye	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
48	L50	2	("6727296").PN.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
49	L51	1	50 and block	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
50	L52	3	("7004579").PN.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
51	L53	2	("20020032252").PN.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
52	L54	249	(inkejt or ink).ti. and dye and 8 and 10	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB

	Type	L #	Hits	Search Text	DBs
55	BRS	L57	4293 7	colored near5 (polymer or resin or particle or block or copolymer or particulate)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
56	BRS	L58	3899 23	block near5 (polymer or copolymer) or diblock or triblock or ab! or bab! or aba!	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
57	BRS	L59	2746 1	(disperse or (oil or solvent) near3 soluble) near5 dye or solvent adj dye	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
58	BRS	L60	0	((inkjet or ink) same 57 same 58 same 59 same (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
59	BRS	L61	0	(57 same 58 same 59 same (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
60	BRS	L63	1	((inkjet or ink) same 57 same 58 same 59 same water same solvent).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	Type	L #	Hits	Search Text	DBs
61	BRS	L64	0	((inkjet or ink) and 57 and 58 and 59 and (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
62	BRS	L65	2	((inkjet or ink) and 57 and 58 and 59 and water same solvent).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
63	BRS	L66	0	(57 and 58 and 59 and (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
64	BRS	L67	0	((inkjet or ink) same 57 same 58 same dye same (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
65	BRS	L68	0	(57 same 58 same dye same (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
66	BRS	L69	0	((inkjet or ink) same 58 same 59 same (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	Type	L #	Hits	Search Text	DBs
67	BRS	L70	1	((inkjet or ink) same 57 same 59 same (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
68	BRS	L71	0	(58 same 59 same (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
69	BRS	L72	1	(57 same 59 same (emuslif$7 or emulsify$3)).clm.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB